


**TEST REPORT**

NUMBER : DELH23002487-EO  
DATE : 29<sup>TH</sup> APRIL, 2023





**TEST REPORT**

NUMBER : DELH23002487-EO  
DATE : 29<sup>TH</sup> APRIL, 2023

AUTHORIZED BY  
FOR INTERTEK INDIA PVT. LTD.

*Kamal Sardhana*

KAMAL SARDHANA  
ASST. MANAGER - HARDLINE

**Testing Remark:** Blush, Moonlight test results have been incorporated from report no. DELH23002487 & / Mint plastic test results have been incorporated from report no. DELH23002488 as per applicant's request.



**TEST REPORT**

NUMBER : DELH23002487-EO  
DATE : 29<sup>TH</sup> APRIL, 2023

**TEST CONDUCTED:**

**1. TOTAL LEAD CONTENT:**

**Test Regulation:** EC No. 1907/2006 (REACH) And Its Amendments, Annex XVII, Entry 63

**Method:** Analysis Was Performed By ICP-MS/AAS

Tested Component	Test Result (ppm)	Requirement
Submitted Sample	<b>COMPLIES</b> Blush plastic: <10 ppm Moonlight plastic: <10 ppm Mint plastic: <10 ppm	500 ppm

Detection Limit: 10 ppm

**2. TOTAL CADMIUM CONTENT:**

**Test Regulation:** EC No. 1907/2006 (REACH) And Its Amendments, Annex XVII, Entry 23

**Method:** Analysis Was Performed By ICP-OES

Tested Component	Test Result (ppm)	Requirement
Submitted Sample	<b>COMPLIES</b> Blush plastic: <10 ppm Moonlight plastic: <10 ppm Mint plastic: <10 ppm	100 ppm

Detection Limit: 10 ppm

**3. BISPHENOL-A CONTENT:**

**Method:** By Solvent Extraction Followed By LC-MS/MS.

Tested Sample	Test Result (ppm) (1,2 & 3)	Requirement
Submitted Sample	<b>COMPLIES</b> Not Detected	Shall Not Contain Any Detectable Levels of Bisphenol-A (BPA)

Detection Limit: 0.1 ppm

**Tested Item:**

1. Blush plastic
2. Moonlight plastic
3. Mint plastic

**4. DISHWASHER SAFE TEST:**

**Method:** As Per Intertek In-House Test Method (M0001-V05)

**Test Condition:**

Selected Cycle: Normal  
Cycle Duration: 120 Minutes  
Temperature Condition: 60°C  
Detergent Used: Cascade  
No. Of cycles: 10 Cycles

Tested Sample	Test Results / Observation (1,2 & 3)	Requirement
Submitted Sample	<b>COMPLIES</b> (No visual change observed)	Shall not show any chipping, cracking, glaze crazing or other visual change in appearance.

**Tested Item:**

1. Blush plastic
2. Moonlight plastic
3. Mint plastic



**TEST REPORT**

NUMBER : DELH23002487-EO  
DATE : 29<sup>TH</sup> APRIL, 2023

**5. OVERALL MIGRATION:**

As Per European Commission Regulation (EC) No.1935/2004 and (EU) No. 10/2011, EU 2020/1245- On Plastic Materials and Articles Intended to Come into Contact with Food)

**Test Method:** With Reference to EN 1186-1:2002 For Selection of Test Condition and Test Method.

Simulant Used	Test Condition	Test Results (mg/dm <sup>2</sup> ) (1,2 & 3)	Requirement (mg/dm <sup>2</sup> )
10% Ethanol	70°C for 2 Hours	< 5.0	10
3% Acetic Acid	70°C for 2 Hours	< 5.0	10
95% Ethanol	60°C for 2 Hours	< 5.0	10
Iso-Octane	40°C for 30 Minutes	< 5.0	10

**Tested Item:**

1. Blush plastic
2. Moonlight plastic
3. Mint plastic

**6. SPECIFIC MIGRATION OF HEAVY METAL (19 ELEMENTS):**

As Per European Commission Regulation (EC) No.1935/2004 and (EU) No.10/2011, EU 2020/1245- On Plastic Materials and Articles Intended to Come into Contact with Food.

**Method:** With Reference to 13130-1:2004, Analysis Was Performed by ICP-MS/OES.

**Simulant Used:** 3% Acetic Acid

**Test Condition:** 70°C for 2 Hours

Test Parameter	Test Result (mg/kg) (1,2 & 3)			Requirement (mg/kg)
	1 <sup>st</sup> Migration	2 <sup>nd</sup> Migration	3 <sup>rd</sup> Migration	
Barium (Ba)	<0.1	<0.1	<0.1	1.0
Aluminum (Al)	<0.1	<0.1	<0.1	1.0
Cobalt (Co)	<0.03	<0.03	<0.03	0.05
Nickel (Ni)	<0.01	<0.01	<0.01	0.02
Copper (Cu)	<1	<1	<1	5.0
Iron (Fe)	<5	<5	<5	48.0
Zinc (Zn)	<1.0	<1.0	<1.0	5.0
Manganese (Mn)	<0.1	<0.1	<0.1	0.6
Lithium (Li)	<0.1	<0.1	<0.1	0.6
Chromium (Cr)	<0.01	<0.01	<0.01	0.01
Antimony (Sb)	<0.01	<0.01	<0.01	0.04
Arsenic (As)	<0.010	<0.010	<0.010	0.01
Cadmium (Cd)	<0.002	<0.002	<0.002	0.002
Lead (Pb)	<0.01	<0.01	<0.01	0.01
Mercury (Hg)	<0.01	<0.01	<0.01	0.01
Europium (Eu)	<0.01	<0.01	<0.01	0.05 (Sum)
Gadolinium (Gd)	<0.01	<0.01	<0.01	
Lanthanum (La)	<0.01	<0.01	<0.01	
Terbium (Tb)	<0.01	<0.01	<0.01	

**Tested Item:**

1. Blush plastic
2. Moonlight plastic
3. Mint plastic

**Note:**

Result of 3rd migration < SML, and

Result of 1st migration ≥ 2nd migration ≥ 3rd migration after consideration of result uncertainty.

Result of 1st, 2nd and 3rd migration < SML when SML limit is Not Detected (ND)



**TEST REPORT**

NUMBER : DELH23002487-EO  
DATE : 29<sup>TH</sup> APRIL, 2023

\*\*\*\*\*

**# END OF TEST REPORT #**

*This report is made solely based on your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis, and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.*

