

TEST REPORT



ORIGINAL SAMPLES



TEST REPORT

APPLICANT: ALL TIME PLASTICS PVT. LTD. / DAMAN
KACHIGA, CHAR RASTA, BEHIND STONE QUARY DAMAN (U.) 396210
ATTN: ZARIR PATEL / JYOTI

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE – EASY CHOP (390 X 210 MM)
(ASSORTED) (48 PC PK)

DATE RECEIVED : 16TH OCT, 2020
BUYER'S NAME : --
BUYING AGENT/ CONTACT : --
ORDER NO. : DAM-PO-GL-1920-900 DT. 26.12.2019
BARCODE : 8902084002319
STYLE NO. : 400231
COLOR : --
END USE : --
SEASON : --
COUNTRY OF ORIGIN : INDIA
COUNTRY OF DESTINATION : INDIA
MANUFACTURER'S NAME : ALL TIME PLASTICS PVT. LTD
CONTENT : --

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).


CONCLUSION:

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
SUBMITTED SAMPLE	DISHWASHER SAFE TEST (IN-HOUSE TEST METHOD)	M
	BISPHENOL-A CONTENT (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)	M
	OVERALL MIGRATION TEST (IS 9845)	M
	TOTAL LEAD CONTENT (AS PER EPA 3050B)	#
	TOTAL CADMIUM CONTENT (AS PER EPA 3050B)	#

NOTE: M = MEET CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT

F = BELOW CLIENT'S REQUIREMENT
N/A = NOT APPLICABLE

PREPARED & CHECKED BY
for INTERTEK INDIA PVT. LTD



SANJAY SADANA
TECHNICAL MANAGER – HARDLINE

TEST REPORT

TEST CONDUCTED:

1. DISHWASHER SAFE TEST:

(REFERENCE: IN-HOUSE TEST METHOD)

TESTING CONDITIONS:

- (1) SELECTED CYCLE: NORMAL
- (2) CYCLE DURATION: 120 MINUTES (APROX.)
- (3) TEMPERATURE CONDITION: 60°C (APROX.)
- (4) NO. OF CYCLES: 10

<u>TESTED COMPONENT</u>	<u>RESULTS</u>	<u>CLIENT'S REQUIREMENT</u>
TURQUOISE CHOPPING BOARD	COMPLIES NO VISUAL CHANGE OBSERVED	Shall not show any chipping, cracking, glaze crazing or other visual change in appearance.

2. BISPHENOL-A CONTENT:

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS ANALYSIS)

<u>TESTED PART</u>	<u>OBSERVATION</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	COMPLIES TURQUOISE PLASTIC: Not Detected WHITE PLASTIC: Not Detected	Shall Not Contain Any Detectable Levels Of Bisphenol-A (BPA)

DETECTION LIMIT: 0.1 ppm

3. OVERALL MIGRATION TEST

(TEST METHOD- IS 9845)

TEST CONDITIONS AND RESULTS:

<u>MATERIAL PUT INTO CONTACT</u>	<u>SIMULANT USED</u>	<u>TEST CONDITION</u>	<u>RESULT IN (mg/dm²)</u>	<u>MAX. LIMIT (mg/dm²)</u>
SUBMITTED SAMPLE- TURQUOISE PLASTIC	3% Acetic acid	70°C for 2 HOURS	<5	<10
	10% Ethanol & H ₂ O	70°C for 2 HOURS	<5	<10
	95% Ethanol	60°C for 4 HOURS	<5	<10
	Iso-Octane	40°C for 30 MINS	<5	<10



TEST REPORT

<u>MATERIAL PUT INTO CONTACT</u>	<u>SIMULANT USED</u>	<u>TEST CONDITION</u>	<u>RESULT IN (mg/dm²)</u>	<u>MAX. LIMIT (mg/dm²)</u>
SUBMITTED SAMPLE- WHITE PLASTIC	3% Acetic acid	70°C for 2 HOURS	<5	<10
	10% Ethanol & H ₂ O	70°C for 2 HOURS	<5	<10
	95% Ethanol	60°C for 4 HOURS	<5	<10
	Iso-Octane	40°C for 30 MINS	<5	<10

REMARK: <= LESS THAN
RESULTS ARE GIVEN IN mg/dm²

4. LEAD CONTENT
(AS PER EPA 3050B)

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	WHITE PLASTIC: <10 PPM TURQUOISE PLASTIC: <10 PPM	NOT PROVIDED

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION

5. CADMIUM CONTENT
(AS PER EPA 3050B)

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	WHITE PLASTIC: <10 PPM TURQUOISE PLASTIC: <10 PPM	NOT PROVIDED

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

