

NUMBER: DELH20012698-D

DATE : 18th OCT, 2020



Page 1 of 5



Intertek India Private Ltd. 290, Udyog Vihar, Phase-II, Gurgaon, Haryana -122016. Tel: 0124-4503400, Fax: 0124-4303592. Registered Office: E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site: www.intertek-labtest.com.



NUMBER: DELH20012698-D

DATE : 18th OCT, 2020

APPLICANT: ALL TIME PLASTICS PVT. LTD./ DAMAN KACHIGAM, CHAR RASTA, BEHIND STONE QUARY DAMAN (U.) 396210

ATTN: ZARIR PATEL / JYOTI

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE –CLASSIC MIXING BOWL 22CM (3200 ML) PURPLE

:
:
:
: DAM-PO-GL-1920-900 DT. 26.12.2019
: 8902084049727
,
: 404972
:
:
:
: INDIA
: INDIA
: ALL TIME PLASTICS PVT. LTD
:

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

CONCLUSION:

TESTED SAMPLE	STANDARD	<u>RESULT</u>
	DISHWASHER SAFE TEST (IN-HOUSE TEST METHOD)	М
	BISPHENOL-A CONTENT (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)	М
	OVERALL MIGRATION TEST (IS 9845)	М
SUBMITTED SAMPLE	TOTAL LEAD CONTENT (AS PER EPA 3050B)	#
	TOTAL CADMIUM CONTENT (AS PER EPA 3050B)	#
	FREEZER TEST (AS PER IN HOUSE TEST METHOD)	М
	MICROWAVE TEST (AS PER IN HOUSE TEST METHOD)	М
	CLIENT'S REQUIREMENT F = BELOW CLIENT'S REQUIRE PECIFIED REQUIREMENT N/A = NOT APPLICATION	

TESTING REMARK: AS CONFIRMED BY APPLICANT BOTH OF PRODUCT MADE BY SAME MATERIALS, NO TESTING CONDUCTED IN THIS TEST REPORT RESULT HAS BEEN INCORPORATED FROM REPORT NO. DELH19014683 AS PER APPLICANT'S REQUEST



(n)

Intertek India Private Ltd.



NUMBER: DELH20012698-D

DATE : 18TH OCT, 2020

PREPARED & CHECKED BY for INTERTEK INDIA PVT. LTD

Sodame

SANJAY SADANA TECHNICAL MANAGER – HARDLINE

TEST CONDUCTED:

1. DISHWASHER SAFE TEST:

(REFERENCE: IN-HOUSE TEST METHOD)

TESTING CONDITIONS:

- (1) SELECTED CYCLE: NORMAL
- (2) CYCLE DURATION: 120 MINUTES (APROX.)
- (3) TEMPERATURE CONDITION: 60°C (APROX.)
- (4) NO. OF CYCLES: 10

TESTED COMPONENT	RESULTS	CLIENT'S REQUIREMENT
SUBMITTED SAMPLE	COMPLIES NO VISUAL CHANGE OBSERVED	Shall not show any chipping, cracking, glaze crazing or other visual change in appearance.

2. BISPHENOL-A CONTENT:

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)

TESTED PART	OBSERVATION	CLIENT'S REQUIREMENT
SUBMITTED SAMPLE	COMPLIES PLASTIC: Not Detected	Shall Not Contain Any Detectable Levels Of Bisphenol-A (BPA)

DETECTION LIMIT: 0.1 ppm

3. OVERALL MIGRATION TEST

(TEST METHOD: IS 9845)

TEST CONDITIONS AND RESULTS:

<u>MATERIAL PUT</u> INTO CONTACT	SIMULANT USED	TEST CONDITION	RESULT IN (mg/dm ²)	<u>MAX. LIMIT</u> (<u>mg/dm²)</u>
	3% Acetic acid	70°C for 2 HRS	<5	<10
SUBMITTED	10% Ethanol	70°C for 2 HRS	<5	<10
SAMPLE	95% Ethanol	60°C for 4 HRS	<5	<10
	Iso-Octane	40°C for 30 MIN	<5	<10







NUMBER: DELH20012698-D

DATE : 18th OCT, 2020

REMARK: <= LESS THAN RESULTS ARE GIVEN IN mg/dm²

4. LEAD CONTENT

(AS PER EPA 3050B)

TESTED SAMPLE	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	PLASTIC: <10 PPM	NOT PROVIDED
ND= NOT DETECTED DETECTION LIMIT = 10 ppr	n	

ppm = PARTS PER MILLION

5. CADMIUM CONTENT

(AS PER EPA 3050B)

TESTED SAMPLE	<u>RESULT (ppm)</u>	CLIENT'S REQUIREMENT
SUBMITTED SAMPLE	PLASTIC: <10 PPM	NOT PROVIDED
ND= NOT DETECTED		

DETECTION LIMIT = 10 ppm ppm = PARTS PER MILLION

6. FREEZER TEST

(AS PER IN HOUSE TEST METHOD)

TESTING CONDITIONS:

- 1 FREEZER TEMPARATURE: 0 °F
- 2 EXPOSURE PERIOD: 24 HOURS

TESTED SAMPLE	RESULTS	REQUIREMENT
SUBMITTED SAMPLE	COMPLIES (No visual change observed)	SHALL NOT SHOW ANY DISCOLORATION, DEFORMATION, CRACKING, CRAZING, CHIPPING OR OTHER CHANGE FROM THE ORIGINAL STATE.

7. MICROWAVE TEST

(AS PER IN HOUSE TEST METHOD)

Page 4 of 5



Intertek India Private Ltd.

290, Udyog Vihar, Phase-II, Gurgaon, Haryana -122016. Tel: 0124-4503400, Fax: 0124-4303592.

Registered Office: E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site: www.intertek-labtest.com.



NUMBER: DELH20012698-D

DATE : 18th OCT, 2020

TESTED SAMPLE	RESULTS	REQUIREMENT
SUBMITTED SAMPLE	COMPLIES (No visual change observed)	SHALL NOT SHOW ANY CHIPPING, CRACKING, CRAZING OR OTHER CHANGE FROM THE ORIGINAL STATE IS RATED AS A FAILURE.

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

Page 5 of 5

