

**TEST REPORT**



**ORIGINAL SAMPLE**



**TEST REPORT**

**APPLICANT: ALL TIME PLASTICS PVT.LTD.**  
PLOT NO. 377/1/1&2), KACHIGAM, CHAR RASTA, DAMAN - 396210

**ATTN: ZARIR PATEL**

SAMPLE DESCRIPTION: CHOPPING BOARD 040 (340 X 240 X 6 MM) (ASSORTED)

DATE RECEIVED : 29<sup>TH</sup> AUG, 2021  
BUYER'S NAME : --  
BUYING AGENT/ CONTACT : --  
ITEM CODE : 408197-24  
HSN CODE : 39241090  
BARCODE : --  
COLOR : AQUIFER  
END USE : --  
COUNTRY OF ORIGIN : --  
COUNTRY OF DESTINATION : --  
MANUFACTURER'S NAME : ALL TIME PLASTICS PVT. LTD.

**TESTS CONDUCTED:** AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

**CONCLUSION:**

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
<b>SUBMITTED SAMPLE</b>	<b>TOTAL LEAD CONTENT</b> (WITH REFERENE TO REGULATION (EC) NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63)	<b>M</b>
	<b>TOTAL CADMIUM CONTENT</b> (AS PER EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23)	<b>M</b>
	<b>BISPHENOL-A CONTENT TEST</b> (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)	<b>M</b>
	<b>DISHWASHER SAFE TEST</b> (AS PER IN-HOUSE TEST METHOD)	<b>M</b>
	<b>OVERALL MIGRATION</b> (IS 9845)	<b>M</b>
	<b>SPECIFIC MIGRATION OF HEAVY METALS</b> (IS 9845)	<b>M</b>

NOTE: M = MEET CLIENT'S REQUIREMENT F = BELOW CLIENT'S REQUIREMENT  
# = NO SPECIFIED REQUIREMENT N/A = NOT APPLICABLE

REMARK: AS PER SUPPLIER DECLARATION SAME MATERIAL HAS BEEN USED & TESTED IN REPORT NO. DELH21011902, HENCE TEST RESULT HAS BEEN REFERRED FROM THE SAME REPORT.

FOR INTERTEK INDIA PVT. LTD

*Sanjay Sadana*

SANJAY SADANA  
TECHNICAL MANAGER – HARDLINE

**TEST REPORT**

**TEST CONDUCTED:**

**1. TOTAL LEAD CONTENT IN SUBSTRATE**

TEST REGULATION: WITH REFERENCE TO EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63

TEST METHOD: ANALYSIS WAS PERFORMED BY ICP-MS/AAS

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	AQUIFER PLASTIC: <10 PPM	< 500 PPM

**REMARK:** ND = NOT DETECTED  
DETECTION LIMIT = 10 PPM  
\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 63

**2. TOTAL CADMIUM CONTENT IN SUBSTRATE**

TEST REGULATION: EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23

TEST METHOD: WITH REF. TO EN112-ANALYSIS WAS PERFORMED BY ICP-MS/AAS

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	AQUIFER PLASTIC: <10 PPM	<100 PPM

**REMARK:** ND = NOT DETECTED  
DETECTION LIMIT = 10 PPM  
\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 23

**3. BISPHENOL-A CONTENT TEST:**

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)

<u>TESTED COMPONENT</u>	<u>RESULTS</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	<b>COMPLIES</b> AQUIFER PLASTIC: ND	SHALL NOT CONTAIN ANY DETECTABLE LEVELS OF BISPHENOL A (BPA)

DETECTION LIMIT: 0.1 PPM

**TEST REPORT**

**4. DISHWASHER SAFE TEST:**

REFERENCE: IN-HOUSE TEST METHOD

TESTING CONDITIONS:

- (1) SELECTED CYCLE: NORMAL
- (2) CYCLE DURATION: 120 MINUTES (APROX.)
- (3) TEMPERATURE CONDITION: 60°C (APROX.)
- (4) DETERGENT USED: CASCADE
- (5) NO. OF CYCLES: 10 CYCLES

<u>TESTED SAMPLE</u>	<u>OBSERVATION</u>	<u>REQUIREMENT</u>
<b>SUBMITTED SAMPLE</b>	<b>COMPLIES</b> NO VISUAL CHANGE OBSERVED	SHALL NOT SHOW ANY CHIPPING, CRACKING, GLAZE CRAZING OR OTHER VISUAL CHANGE IN APPEARANCE.

**5. OVERALL MIGRATION TEST:**

TEST METHOD: IS 9845

**TEST CONDITIONS AND RESULTS:**

<b>MATERIAL PUT INTO CONTACT</b>	<b>SIMULANT USED</b>	<b>TEST CONDITION</b>	<b>RESULT IN (mg/dm<sup>2</sup>)</b>	<b>MAX. LIMIT (mg/dm<sup>2</sup>)</b>
			[1]	
<b>MATERIAL PUT INTO CONTACT</b>	3% ACITIC ACID	70 °C FOR 02 HOURS	<5	<10
	10% ETHANOL	70 °C FOR 02 HOURS	<5	<10
	95% ETHANOL	60 °C FOR 02 HOURS	<5	<10
	ISO- OCTANE	40°C FOR 30 MIN.	<5	<10

**REMARK:** <= LESS THAN

RESULTS ARE GIVEN IN mg/dm<sup>2</sup>= Milligram per decimeter square

**TESTED COMPONENT:**

1. AQUIFER CHOPPING BOARD

**TEST REPORT**

**6. SPECIFIC MIGRATION OF HEAVY METALS TEST:**

TEST METHOD: IS 9845

TEST CONDITION: 3% ACITIC ACID AT 70°C FOR 02 HOUR.

ELEMENT	RESULTS (mg/ kg)	MAX. PERMISSIBLE LIMIT (mg/ kg)
	[1]	
Barium (Ba)	<0.1	1.0
Cobalt (Co)	<0.01	0.05
Copper (Cu)	<1.0	5.0
Iron (Fe)	<5.0	48.0
Lithium (Li)	<0.1	0.6
Manganese (Mn)	<0.1	0.6
Zinc (Zn)	<1.0	25.0
Antimony (Sb)	<0.02	0.04

< = LESS THAN

mg/kg = MILLIGRAM PER KILOGRAM

**TESTED COMPONENT:**

1. AQUIFER CHOPPING BOARD

\*\*\*\*\*

**# END OF TEST REPORT #**


This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.



NUMBER : DELH21011900- K

**TEST REPORT**

DATE : 15<sup>TH</sup> SEP, 2021



**ORIGINAL SAMPLE**



**TEST REPORT**

**APPLICANT:** ALL TIME PLASTICS PVT.LTD.  
PLOT NO. 377/1/1&2), KACHIGAM, CHAR RASTA, DAMAN - 396210

**ATTN:** ZARIR PATEL

SAMPLE DESCRIPTION: CHOPPING BOARD 040 (340 X 240 X 6 MM) (ASSORTED)

DATE RECEIVED : 29<sup>TH</sup> AUG, 2021  
BUYER'S NAME : --  
BUYING AGENT/ CONTACT : --  
ITEM CODE : 408197-24  
HSN CODE : 39241090  
BARCODE : --  
COLOR : BLUSH  
END USE : --  
COUNTRY OF ORIGIN : --  
COUNTRY OF DESTINATION : --  
MANUFACTURER'S NAME : ALL TIME PLASTICS PVT. LTD.

**TESTS CONDUCTED:** AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

**CONCLUSION:**

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
<b>SUBMITTED SAMPLE</b>	<b>TOTAL LEAD CONTENT</b> (WITH REFERENE TO REGULATION (EC) NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63)	<b>M</b>
	<b>TOTAL CADMIUM CONTENT</b> (AS PER EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23)	<b>M</b>
	<b>BISPHENOL-A CONTENT TEST</b> (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)	<b>M</b>
	<b>DISHWASHER SAFE TEST</b> (AS PER IN-HOUSE TEST METHOD)	<b>M</b>
	<b>OVERALL MIGRATION</b> (IS 9845)	<b>M</b>
	<b>SPECIFIC MIGRATION OF HEAVY METALS</b> (IS 9845)	<b>M</b>

NOTE: M = MEET CLIENT'S REQUIREMENT F = BELOW CLIENT'S REQUIREMENT  
# = NO SPECIFIED REQUIREMENT N/A = NOT APPLICABLE

REMARK: AS PER SUPPLIER DECLARATION SAME MATERIAL HAS BEEN USED & TESTED IN REPORT NO. DELH21011900, HENCE TEST RESULT HAS BEEN REFERRED FROM THE SAME REPORT.

FOR INTERTEK INDIA PVT. LTD

*Sanjay Sadana*

SANJAY SADANA  
TECHNICAL MANAGER – HARDLINE

**TEST REPORT**

**TEST CONDUCTED:**

**1. TOTAL LEAD CONTENT IN SUBSTRATE**

TEST REGULATION: WITH REFERENCE TO EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63

TEST METHOD: ANALYSIS WAS PERFORMED BY ICP-MS/AAS

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	BLUSH PLASTIC: <10 PPM	< 500 PPM

**REMARK:** ND = NOT DETECTED  
DETECTION LIMIT = 10 PPM  
\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 63

**2. TOTAL CADMIUM CONTENT IN SUBSTRATE**

TEST REGULATION: EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23

TEST METHOD: WITH REF. TO EN112-ANALYSIS WAS PERFORMED BY ICP-MS/AAS

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	BLUSH PLASTIC: <10 PPM	<100 PPM

**REMARK:** ND = NOT DETECTED  
DETECTION LIMIT = 10 PPM  
\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 23

**3. BISPHENOL-A CONTENT TEST:**

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)

<u>TESTED COMPONENT</u>	<u>RESULTS</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	<b>COMPLIES</b> BLUSH PLASTIC: ND	SHALL NOT CONTAIN ANY DETECTABLE LEVELS OF BISPHENOL A (BPA)

DETECTION LIMIT: 0.1 PPM





**TEST REPORT**

**4. DISHWASHER SAFE TEST:**

REFERENCE: IN-HOUSE TEST METHOD

TESTING CONDITIONS:

- (1) SELECTED CYCLE: NORMAL
- (2) CYCLE DURATION: 120 MINUTES (APROX.)
- (3) TEMPERATURE CONDITION: 60°C (APROX.)
- (4) DETERGENT USED: CASCADE
- (5) NO. OF CYCLES: 10 CYCLES

<u>TESTED SAMPLE</u>	<u>OBSERVATION</u>	<u>REQUIREMENT</u>
<b>SUBMITTED SAMPLE</b>	<b>COMPLIES</b> NO VISUAL CHANGE OBSERVED	SHALL NOT SHOW ANY CHIPPING, CRACKING, GLAZE CRAZING OR OTHER VISUAL CHANGE IN APPEARANCE.

**5. OVERALL MIGRATION TEST:**

TEST METHOD: IS 9845

**TEST CONDITIONS AND RESULTS:**

	<b>SIMULANT USED</b>	<b>TEST CONDITION</b>	<b>RESULT IN (mg/dm<sup>2</sup>)</b>	<b>MAX. LIMIT (mg/dm<sup>2</sup>)</b>
			[1]	
<b>MATERIAL PUT INTO CONTACT</b>	3% ACITIC ACID	70 °C FOR 02 HOURS	<5	<10
	10% ETHANOL	70 °C FOR 02 HOURS	<5	<10
	95% ETHANOL	60 °C FOR 02 HOURS	<5	<10
	ISO- OCTANE	40°C FOR 30 MIN.	<5	<10

**REMARK:** <= LESS THAN

RESULTS ARE GIVEN IN mg/dm<sup>2</sup>= Milligram per decimeter square

**TESTED COMPONENT:**

1. BLUSH CHOPPING BOARD

**TEST REPORT**

**6. SPECIFIC MIGRATION OF HEAVY METALS TEST:**

TEST METHOD: IS 9845

TEST CONDITION: 3% ACITIC ACID AT 70°C FOR 02 HOUR.

ELEMENT	RESULTS (mg/ kg)	MAX. PERMISSIBLE LIMIT (mg/ kg)
	[1]	
Barium (Ba)	<0.1	1.0
Cobalt (Co)	<0.01	0.05
Copper (Cu)	<1.0	5.0
Iron (Fe)	<5.0	48.0
Lithium (Li)	<0.1	0.6
Manganese (Mn)	<0.1	0.6
Zinc (Zn)	<1.0	25.0
Antimony (Sb)	<0.02	0.04

< = LESS THAN

mg/kg = MILLIGRAM PER KILOGRAM

**TESTED COMPONENT:**


1. BLUSH CHOPPING BOARD

\*\*\*\*\*

**# END OF TEST REPORT #**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

**TEST REPORT**



**ORIGINAL SAMPLE**

**TEST REPORT**

**APPLICANT: ALL TIME PLASTICS PVT.LTD.**  
PLOT NO. 377/1/1&2), KACHIGAM, CHAR RASTA, DAMAN - 396210

**ATTN: ZARIR PATEL**

SAMPLE DESCRIPTION: CHOPPING BOARD 040 (340 X 240 X 6 MM) (ASSORTED)

DATE RECEIVED : 29<sup>TH</sup> AUG, 2021  
BUYER'S NAME : --  
BUYING AGENT/ CONTACT : --  
ITEM CODE : 408197-24  
HSN CODE : 39241090  
BARCODE : --  
COLOR : INDIGO  
END USE : --  
COUNTRY OF ORIGIN : --  
COUNTRY OF DESTINATION : --  
MANUFACTURER'S NAME : ALL TIME PLASTICS PVT. LTD.

**TESTS CONDUCTED:** AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

**CONCLUSION:**

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
<b>SUBMITTED SAMPLE</b>	<b>TOTAL LEAD CONTENT</b> (WITH REFERENE TO REGULATION (EC) NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63)	<b>M</b>
	<b>TOTAL CADMIUM CONTENT</b> (AS PER EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23)	<b>M</b>
	<b>BISPHENOL-A CONTENT TEST</b> (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)	<b>M</b>
	<b>DISHWASHER SAFE TEST</b> (AS PER IN-HOUSE TEST METHOD)	<b>M</b>
	<b>OVERALL MIGRATION</b> (IS 9845)	<b>M</b>
	<b>SPECIFIC MIGRATION OF HEAVY METALS</b> (IS 9845)	<b>M</b>

NOTE: M = MEET CLIENT'S REQUIREMENT F = BELOW CLIENT'S REQUIREMENT  
# = NO SPECIFIED REQUIREMENT N/A = NOT APPLICABLE

REMARK: AS PER SUPPLIER DECLARATION SAME MATERIAL HAS BEEN USED & TESTED IN REPORT NO. DELH21011901, HENCE TEST RESULT HAS BEEN REFERRED FROM THE SAME REPORT.

FOR INTERTEK INDIA PVT. LTD

*Sanjay Sadana*

SANJAY SADANA  
TECHNICAL MANAGER – HARDLINE

**TEST REPORT**

**TEST CONDUCTED:**

**1. TOTAL LEAD CONTENT IN SUBSTRATE**

TEST REGULATION: WITH REFERENCE TO EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63

TEST METHOD: ANALYSIS WAS PERFORMED BY ICP-MS/AAS

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	INDIGO PLASTIC: <10 PPM	< 500 PPM

**REMARK:** ND = NOT DETECTED  
DETECTION LIMIT = 10 PPM  
\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 63

**2. TOTAL CADMIUM CONTENT IN SUBSTRATE**

TEST REGULATION: EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23

TEST METHOD: WITH REF. TO EN112-ANALYSIS WAS PERFORMED BY ICP-MS/AAS

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	INDIGO PLASTIC: <10 PPM	<100 PPM

**REMARK:** ND = NOT DETECTED  
DETECTION LIMIT = 10 PPM  
\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 23

**3. BISPHENOL-A CONTENT TEST:**

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)

<u>TESTED COMPONENT</u>	<u>RESULTS</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	<b>COMPLIES</b> INDIGO PLASTIC: ND	SHALL NOT CONTAIN ANY DETECTABLE LEVELS OF BISPHENOL A (BPA)

DETECTION LIMIT: 0.1 PPM

**TEST REPORT**

**4. DISHWASHER SAFE TEST:**

REFERENCE: IN-HOUSE TEST METHOD

TESTING CONDITIONS:

- (1) SELECTED CYCLE: NORMAL
- (2) CYCLE DURATION: 120 MINUTES (APROX.)
- (3) TEMPERATURE CONDITION: 60°C (APROX.)
- (4) DETERGENT USED: CASCADE
- (5) NO. OF CYCLES: 10 CYCLES

<u>TESTED SAMPLE</u>	<u>OBSERVATION</u>	<u>REQUIREMENT</u>
<b>SUBMITTED SAMPLE</b>	<b>COMPLIES</b>  NO VISUAL CHANGE OBSERVED	SHALL NOT SHOW ANY CHIPPING, CRACKING, GLAZE CRAZING OR OTHER VISUAL CHANGE IN APPEARANCE.

**5. OVERALL MIGRATION TEST:**

TEST METHOD: IS 9845

**TEST CONDITIONS AND RESULTS:**

	<b>SIMULANT USED</b>	<b>TEST CONDITION</b>	<b>RESULT IN (mg/dm<sup>2</sup>)</b>	<b>MAX. LIMIT (mg/dm<sup>2</sup>)</b>
			[1]	
<b>MATERIAL PUT INTO CONTACT</b>	3% ACITIC ACID	70 °C FOR 02 HOURS	<5	<10
	10% ETHANOL	70 °C FOR 02 HOURS	<5	<10
	95% ETHANOL	60 °C FOR 02 HOURS	<5	<10
	ISO- OCTANE	40°C FOR 30 MIN.	<5	<10

**REMARK:** <= LESS THAN

RESULTS ARE GIVEN IN mg/dm<sup>2</sup>= Milligram per decimeter square

**TESTED COMPONENT:**

1. INDIGO CHOPPING BOARD



**TEST REPORT**

**6. SPECIFIC MIGRATION OF HEAVY METALS TEST:**

TEST METHOD: IS 9845

TEST CONDITION: 3% ACITIC ACID AT 70°C FOR 02 HOUR.

ELEMENT	RESULTS (mg/ kg)	MAX. PERMISSIBLE LIMIT (mg/ kg)
	[1]	
Barium (Ba)	<0.1	1.0
Cobalt (Co)	<0.01	0.05
Copper (Cu)	<1.0	5.0
Iron (Fe)	<5.0	48.0
Lithium (Li)	<0.1	0.6
Manganese (Mn)	<0.1	0.6
Zinc (Zn)	<1.0	25.0
Antimony (Sb)	<0.02	0.04

< = LESS THAN

mg/kg = MILLIGRAM PER KILOGRAM

**TESTED COMPONENT:**

1. INDIGO CHOPPING BOARD

\*\*\*\*\*

**# END OF TEST REPORT #**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

