

TEST REPORT



ORIGINAL SAMPLE



TEST REPORT

APPLICANT: ALL TIME PLASTICS PVT. LTD. / DAMAN
KACHIGAM, CHAR RASTA, BEHIND STONE QUARY DAMAN (U.) 396210

ATTN: ZARIR PATEL / JYOTI

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE –
FOOD SAVER CONTAINER 7000H (7000 ml) – GREEN

BUYER'S NAME : --
BUYING AGENT/ CONTACT : --
ORDER NO. : DAM-PO-GL-1920-900 DT.26.12.2019
BARCODE : 8902084062238
STYLE NO. : 406223
COLOR : --
END USE : --
SEASON : --
COUNTRY OF ORIGIN : INDIA
COUNTRY OF DESTINATION : INDIA
MANUFACTURER'S NAME : ALL TIME PLASTICS PVT. LTD.
CONTENT : --

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).


CONCLUSION:

| TESTED SAMPLE | STANDARD | RESULT |
|-------------------------|--|---------------|
| SUBMITTED SAMPLE | DISHWASHER SAFE TEST (IN-HOUSE TEST METHOD) | M |
| | BISPHENOL-A CONTENT (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS) | M |
| | OVERALL MIGRATION TEST (IS 9845) | M |
| | TOTAL LEAD CONTENT (AS PER EPA 3050B) | # |
| | TOTAL CADMIUM CONTENT (AS PER EPA 3050B) | # |
| | FREEZER TEST (AS PER IN HOUSE TEST METHOD) | M |
| | MICROWAVE TEST (AS PER IN HOUSE TEST METHOD) | M |

NOTE: M = MEET CLIENT'S REQUIREMENT F = BELOW CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT N/A = NOT APPLICABLE

TESTING REMARK : AS CONFIRMED BY APPLICANT BOTH OF PRODUCT MADE BY SAME MATERIALS, NO TESTING CONDUCTED IN THIS TEST REPORT RESULT HAS BEEN INCORPORATED FROM REPORT NO DELH19014681 AS PER APPLICANT'S REQUEST.

PREPARED & CHECKED BY
for INTERTEK INDIA PVT. LTD



SANJAY SADANA
TECHNICAL MANAGER – HARDLINE



TEST REPORT

TEST CONDUCTED:

1. DISHWASHER SAFE TEST:

(REFERENCE: IN-HOUSE TEST METHOD)

TESTING CONDITIONS:

- (1) SELECTED CYCLE: NORMAL
- (2) CYCLE DURATION: 120 MINUTES (APROX.)
- (3) TEMPERATURE CONDITION: 60°C (APROX.)
- (4) NO. OF CYCLES: 10

| TESTED COMPONENT | RESULTS | CLIENT'S REQUIREMENT |
|-------------------------|--|--|
| SUBMITTED SAMPLE | COMPLIES NO VISUAL CHANGE OBSERVED | Shall not show any chipping, cracking, glaze crazing or other visual change in appearance. |

2. BISPHEENOL-A CONTENT:

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)

| TESTED PART | OBSERVATION | CLIENT'S REQUIREMENT |
|--------------------|--|--|
| SUBMITTED SAMPLE | COMPLIES LID PLASTIC: Not Detected TRANSPARENT BODY PLASTIC: Not Detected | Shall Not Contain Any Detectable Levels Of Bisphenol-A (BPA) |

DETECTION LIMIT: 0.1 ppm

3. OVERALL MIGRATION TEST

(TEST METHOD: IS 9845)

TEST CONDITIONS AND RESULTS:

| MATERIAL PUT INTO CONTACT | SIMULANT USED | TEST CONDITION | RESULT IN (mg/dm²) | MAX. LIMIT (mg/dm²) |
|----------------------------------|----------------------|-----------------------|--------------------------------------|---------------------------------------|
| SUBMITTED SAMPLE | 3% Acetic acid | 40°C for 10 DAYS | <5 | <10 |
| | 10% Ethanol | 40°C for 10 DAYS | <5 | <10 |
| | 95% Ethanol | 40°C for 10 DAYS | <5 | <10 |
| | Iso-Octane | 20°C for 2 DAYS | <5 | <10 |



TEST REPORT

| <u>MATERIAL PUT INTO CONTACT</u> | <u>SIMULANT USED</u> | <u>TEST CONDITION</u> | <u>RESULT IN (mg/dm²)</u> | <u>MAX. LIMIT (mg/dm²)</u> |
|----------------------------------|----------------------|-----------------------|--------------------------------------|---------------------------------------|
| SUBMITTED SAMPLE | 3% Acetic acid | 40°C for 10 DAYS | <5 | <10 |
| | 10% Ethanol | 40°C for 10 DAYS | <5 | <10 |
| | 95% Ethanol | 40°C for 10 DAYS | <5 | <10 |
| | Iso-Octane | 20°C for 2 DAYS | <5 | <10 |

REMARK: <= LESS THAN
RESULTS ARE GIVEN IN mg/dm²

4. LEAD CONTENT
(AS PER EPA 3050B)

| <u>TESTED SAMPLE</u> | <u>RESULT (ppm)</u> | <u>CLIENT'S REQUIREMENT</u> |
|----------------------|---|-----------------------------|
| SUBMITTED SAMPLE | LID PLASTIC: <10 PPM TRANSPARENT PLASTIC BODY: <10 PPM | NOT PROVIDED |

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION

5. CADMIUM CONTENT
(AS PER EPA 3050B)

| <u>TESTED SAMPLE</u> | <u>RESULT (ppm)</u> | <u>CLIENT'S REQUIREMENT</u> |
|----------------------|---|-----------------------------|
| SUBMITTED SAMPLE | LID PLASTIC: <10 PPM TRANSPARENT PLASTIC BODY: <10 PPM | NOT PROVIDED |

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION



TEST REPORT

6. FREEZER TEST
(AS PER IN HOUSE TEST METHOD)

- TESTING CONDITIONS:**
1 FREEZER TEMPARATURE: 0 °F
2 EXPOSURE PERIOD: 24 HOURS

| TESTED SAMPLE | RESULTS | REQUIREMENT |
|------------------|--|---|
| SUBMITTED SAMPLE | COMPLIES (No visual change observed) | SHALL NOT SHOW ANY DISCOLORATION, DEFORMATION, CRACKING, CRAZING, CHIPPING OR OTHER CHANGE FROM THE ORIGINAL STATE. |

7. MICROWAVE TEST
(AS PER IN HOUSE TEST METHOD)

| TESTED SAMPLE | RESULTS | REQUIREMENT |
|------------------|--|---|
| SUBMITTED SAMPLE | COMPLIES (No visual change observed) | SHALL NOT SHOW ANY CHIPPING, CRACKING, CRAZING OR OTHER CHANGE FROM THE ORIGINAL STATE IS RATED AS A FAILURE. |

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

