

TEST REPORT



ORIGINAL SAMPLE



TEST REPORT

APPLICANT: ALL TIME PLASTICS PVT. LTD. / DAMAN
KACHIGAM, CHAR RASTA, BEHIND STONE QUARY DAMAN (U.) 396210

ATTN: ZARIR PATEL / JYOTI

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE – 402642 - Glass 400 ml (2400 ml) (6 Pc Set) TURQUOISE

DATE RECEIVED : 27TH DEC, 2019
BUYER'S NAME : --
BUYING AGENT/ CONTACT : --
ORDER NO. : DAM-PO-GL-1920-900 DT. 26.12.2019
BARCODE : 8902084026421
STYLE NO. : 402642
COLOR : --
END USE : --
SEASON : --
COUNTRY OF ORIGIN : --
COUNTRY OF DESTINATION : --
MANUFACTURER'S NAME : **ALL TIME PLASTICS PVT. LTD**
CONTENT : --

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

CONCLUSION:


| <u>TESTED SAMPLE</u> | <u>STANDARD</u> | <u>RESULT</u> |
|----------------------|--|---------------|
| Submitted sample | BISPHENOL-A CONTENT (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS) | M |
| | OVERALL MIGRATION TEST (IS 9845) | M |
| | TOTAL LEAD CONTENT (AS PER EPA 3050B) | # |
| | TOTAL CADMIUM CONTENT (AS PER EPA 3050B) | # |

NOTE: M = MEET CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT

F = BELOW CLIENT'S REQUIREMENT
N/A = NOT APPLICABLE

TESTING REMARK: AS CONFIRMED BY APPLICANT BOTH OF PRODUCT MADE BY SAME MATERIALS, NO TESTING CONDUCTED IN THIS TEST REPORT RESULT HAS BEEN INCORPORATED FROM REPORT NO. DELH19014674 AS PER APPLICANT'S REQUEST

PREPARED & CHECKED BY
for INTERTEK INDIA PVT. LTD



SANJAY SADANA
TECHNICAL MANAGER – HARDLINE



TEST REPORT

TEST CONDUCTED:

1. BISPHENOL-A CONTENT:

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)

| TESTED PART | OBSERVATION | CLIENT'S REQUIREMENT |
|------------------|--|--|
| SUBMITTED SAMPLE | COMPLIES TURQUOISE PLASTIC: Not Detected | Shall Not Contain Any Detectable Levels Of Bisphenol-A (BPA) |

DETECTION LIMIT: 0.1 ppm

2. OVERALL MIGRATION TEST

(TEST METHOD: IS 9845)

TEST CONDITIONS AND RESULTS:

| <u>MATERIAL PUT INTO CONTACT</u> | <u>SIMULANT USED</u> | <u>TEST CONDITION</u> | <u>RESULT IN (mg/dm²)</u> | <u>MAX. LIMIT (mg/dm²)</u> |
|----------------------------------|--------------------------------|-----------------------|--------------------------------------|---------------------------------------|
| SUBMITTED SAMPLE | 3% Acetic acid | 70°C for 2 HOURS | <5 | <10 |
| | 10% Ethanol & H ₂ O | 70°C for 2 HOURS | <5 | <10 |
| | 95% Ethanol | 60°C for 4 HOURS | <5 | <10 |
| | Iso-Octane | 40°C for 30 MIN | <5 | <10 |

REMARK: <= LESS THAN
RESULTS ARE GIVEN IN mg/dm²

4. LEAD CONTENT

(AS PER EPA 3050B)

| <u>TESTED SAMPLE</u> | <u>RESULT (ppm)</u> | <u>CLIENT'S REQUIREMENT</u> |
|----------------------|----------------------------|-----------------------------|
| SUBMITTED SAMPLE | TURQUOISE PLASTIC: <10 PPM | NOT PROVIDED |

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION



TEST REPORT

3. CADMIUM CONTENT
(AS PER EPA 3050B)

| TESTED SAMPLE | RESULT (ppm) | CLIENT'S REQUIREMENT |
|----------------------|-------------------------------|-----------------------------|
| SUBMITTED SAMPLE | TURQUOISE PLASTIC: <10 PPM | NOT PROVIDED |

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.



TEST REPORT



ORIGINAL SAMPLE

TEST REPORT

APPLICANT: ALL TIME PLASTICS PVT. LTD. / DAMAN
KACHIGA, CHAR RASTA, BEHIND STONE QUARY DAMAN (U.) 396210

ATTN: ZARIR PATEL / JYOTI

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE – 402642 - Glass 400 ml (2400 ml) (6 Pc Set) Purple

DATE RECEIVED : 27TH DEC, 2019
BUYER'S NAME : --
BUYING AGENT/ CONTACT : --
ORDER NO. : DAM-PO-GL-1920-900 DT. 26.12.2019
BARCODE : 8902084026421
STYLE NO. : 402642
COLOR : --
END USE : --
SEASON : --
COUNTRY OF ORIGIN : --
COUNTRY OF DESTINATION : --
MANUFACTURER'S NAME : ALL TIME PLASTICS PVT. LTD
CONTENT : --

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

CONCLUSION:


| <u>TESTED SAMPLE</u> | <u>STANDARD</u> | <u>RESULT</u> |
|-------------------------|--|---------------|
| SUBMITTED SAMPLE | BISPHENOL-A CONTENT (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS) | M |
| | OVERALL MIGRATION TEST (IS 9845) | M |
| | TOTAL LEAD CONTENT (AS PER EPA 3050B) | # |
| | TOTAL CADMIUM CONTENT (AS PER EPA 3050B) | # |

NOTE: M = MEET CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT

F = BELOW CLIENT'S REQUIREMENT
N/A = NOT APPLICABLE

TESTING REMARK: AS CONFIRMED BY APPLICANT BOTH OF PRODUCT MADE BY SAME MATERIALS, NO TESTING CONDUCTED IN THIS TEST REPORT RESULT HAS BEEN INCORPORATED FROM REPORT NO. DELH19014683AS PER APPLICANT'S REQUEST

PREPARED & CHECKED BY
for INTERTEK INDIA PVT. LTD



SANJAY SADANA
TECHNICAL MANAGER – HARDLINE



TEST REPORT

TEST CONDUCTED:

1. BISPHENOL-A CONTENT:

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)

| TESTED PART | OBSERVATION | CLIENT'S REQUIREMENT |
|--------------------|---|--|
| SUBMITTED SAMPLE | COMPLIES Purple PLASTIC: Not Detected | Shall Not Contain Any Detectable Levels Of Bisphenol-A (BPA) |

DETECTION LIMIT: 0.1 ppm

2. OVERALL MIGRATION TEST

(TEST METHOD: IS 9845)

TEST CONDITIONS AND RESULTS:

| <u>MATERIAL PUT INTO CONTACT</u> | <u>SIMULANT USED</u> | <u>TEST CONDITION</u> | <u>RESULT IN (mg/dm²)</u> | <u>MAX. LIMIT (mg/dm²)</u> |
|---|--------------------------------|------------------------------|---|--|
| SUBMITTED SAMPLE | 3% Acetic acid | 70°C for 2 HOURS | <5 | <10 |
| | 10% Ethanol & H ₂ O | 70°C for 2 HOURS | <5 | <10 |
| | 95% Ethanol | 60°C for 4 HOURS | <5 | <10 |
| | Iso-Octane | 40°C for 30 MIN | <5 | <10 |

REMARK: <= LESS THAN
RESULTS ARE GIVEN IN mg/dm²

3. LEAD CONTENT

(AS PER EPA 3050B)

| <u>TESTED SAMPLE</u> | <u>RESULT (ppm)</u> | <u>CLIENT'S REQUIREMENT</u> |
|-----------------------------|----------------------------|------------------------------------|
| SUBMITTED SAMPLE | Purple PLASTIC: <10 PPM | NOT PROVIDED |

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION



TEST REPORT

4. CADMIUM CONTENT
(AS PER EPA 3050B)

| <u>TESTED SAMPLE</u> | <u>RESULT (ppm)</u> | <u>CLIENT'S REQUIREMENT</u> |
|-----------------------------|----------------------------|------------------------------------|
| SUBMITTED SAMPLE | Purple PLASTIC: <10 PPM | NOT PROVIDED |

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.



TEST REPORT



ORIGINAL SAMPLE



TEST REPORT

APPLICANT: ALL TIME PLASTICS PVT. LTD. / DAMAN
KACHIGAM, CHAR RASTA, BEHIND STONE QUARY DAMAN (U.) 396210

ATTN: ZARIR PATEL / JYOTI

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE 402642 - Glass 400 ml (2400 ml) (6 Pc Set) RED

DATE RECEIVED : 27TH DEC, 2019
BUYER'S NAME : --
BUYING AGENT/ CONTACT : --
ORDER NO. : DAM-PO-GL-1920-900 DT. 26.12.2019
BARCODE : 8902084026421
STYLE NO. : 402642
COLOR : --
END USE : --
SEASON : --
COUNTRY OF ORIGIN : --
COUNTRY OF DESTINATION : --
MANUFACTURER'S NAME : **ALL TIME PLASTICS PVT. LTD**
CONTENT : --

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

CONCLUSION:


| <u>TESTED SAMPLE</u> | <u>STANDARD</u> | <u>RESULT</u> |
|-------------------------|--|---------------|
| SUBMITTED SAMPLE | BISPHENOL-A CONTENT (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS) | M |
| | OVERALL MIGRATION TEST (IS 9845) | M |
| | TOTAL LEAD CONTENT (AS PER EPA 3050B) | # |
| | TOTAL CADMIUM CONTENT (AS PER EPA 3050B) | # |

NOTE: M = MEET CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT

F = BELOW CLIENT'S REQUIREMENT
N/A = NOT APPLICABLE

TESTING REMARK: AS CONFIRMED BY APPLICANT BOTH OF PRODUCT MADE BY SAME MATERIALS, NO TESTING CONDUCTED IN THIS TEST REPORT RESULT HAS BEEN INCORPORATED FROM REPORT NO. DELH19014673AS PER APPLICANT'S REQUEST

PREPARED & CHECKED BY
for INTERTEK INDIA PVT. LTD



SANJAY SADANA
TECHNICAL MANAGER – HARDLINE



TEST REPORT

TEST CONDUCTED:

1. BISPHENOL-A CONTENT:

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)

| TESTED PART | OBSERVATION | CLIENT'S REQUIREMENT |
|------------------|--|--|
| SUBMITTED SAMPLE | COMPLIES RED PLASTIC: Not Detected | Shall Not Contain Any Detectable Levels Of Bisphenol-A (BPA) |

DETECTION LIMIT: 0.1 ppm

2. OVERALL MIGRATION TEST

(TEST METHOD: IS 9845)

TEST CONDITIONS AND RESULTS:

| MATERIAL PUT INTO CONTACT | SIMULANT USED | TEST CONDITION | RESULT IN (mg/dm ²) | MAX. LIMIT (mg/dm ²) |
|---------------------------|--------------------------------|------------------|---------------------------------|----------------------------------|
| SUBMITTED SAMPLE | 3% Acetic acid | 70°C for 2 HOURS | <5 | <10 |
| | 10% Ethanol & H ₂ O | 70°C for 2 HOURS | <5 | <10 |
| | 95% Ethanol | 60°C for 4 HOURS | <5 | <10 |
| | Iso-Octane | 40°C for 30 MIN | <5 | <10 |

REMARK: <= LESS THAN
RESULTS ARE GIVEN IN mg/dm²

3. LEAD CONTENT

(AS PER EPA 3050B)

| TESTED SAMPLE | RESULT (ppm) | CLIENT'S REQUIREMENT |
|------------------|----------------------|----------------------|
| SUBMITTED SAMPLE | RED PLASTIC: <10 PPM | NOT PROVIDED |

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION



TEST REPORT

4. CADMIUM CONTENT
(AS PER EPA 3050B)

| TESTED SAMPLE | RESULT (ppm) | CLIENT'S REQUIREMENT |
|----------------------|-------------------------|-----------------------------|
| SUBMITTED SAMPLE | RED PLASTIC: <10 PPM | NOT PROVIDED |

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

