

NUMBER: DELH21013332- H

DATE : 28<sup>TH</sup> SEP, 2021



**ORIGINAL SAMPLE** 





NUMBER: DELH21013332- H

: 28TH SEP, 2021 DATE

APPLICANT: ALL TIME PLASTICS PVT.LTD.

PLOT NO. 377/1/1&2), KACHIGAM, CHAR RASTA, DAMAN - 396210

ATTN: ZARIR PATEL

SAMPLE DESCRIPTION : FROSTEE CONTAINER 950 ML (2850 ML) (ASSORTED) (3 PC SET)

DATE RECEIVED : 25<sup>TH</sup> JULY, 2021

BUYER'S NAME BUYING AGENT/ CONTACT : --

ITEM CODE : 408401-30 HSN CODE : 39241090 BARCODE : 8902084074095 COLOR : INDIGO

END USE : --COUNTRY OF ORIGIN : --COUNTRY OF DESTINATION : --

: ALL TIME PLASTICS PVT. LTD. MANUFACTURER'S NAME

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

#### CONCLUSION:

TESTED SAMPLE	STANDARD	RESULT
	TOTAL LEAD CONTENT (WITH REFERENE TO REGULATION (EC) NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63)	M
	(AS PER EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23)	М
	BISPHENOL-A CONTENT TEST (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)	M
	OVERALL MIGRATION (IS 9845)	М
	SPECIFIC MIGRATION OF HEAVY METALS (IS 9845)	М
SUBMITTED SAMPLE	COLOUR MIGRATION TEST: (AS PER TEST METHOD: IS 9845)	М
	<b>DISHWASHER SAFE TEST</b> (AS PER IN-HOUSE TEST METHOD)	M
	MICROWAVE SAFE TEST (IN-HOUSE TEST METHOD)	M
	FREEZER SAFE TEST (IN-HOUSE TEST METHOD)	M
	AIR TIGHT TEST (IN-HOUSE TEST METHOD)	M



Page 2 of 8



NUMBER: DELH21013332- H

DATE : 28<sup>TH</sup> SEP, 2021

NOTE: M = MEET CLIENT'S REQUIREMENT # = NO SPECIFIED REQUIREMENT F = BELOW CLIENT'S REQUIREMENT

N/A = NOT APPLICABLE

REMARK: AS PER SUPPLIER DECLARATION SAME MATERIAL HAS BEEN USED & TESTED IN REPORT NO. DELH21009914, HENCE TEST RESULT HAS BEEN REFERRED FROM THE SAME REPORT.

FOR INTERTEK INDIA PVT. LTD

SANJAY SADANA

Stodame

TECHNICAL MANAGER - HARDLINE





NUMBER: DELH21013332- H

DATE : 28<sup>TH</sup> SEP, 2021

## **TEST CONDUCTED:**

#### 1. TOTAL LEAD CONTENT IN SUBSTRATE

TEST REGULATION: WITH REFERENCE TO EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63

TEST METHOD: ANALYSIS WAS PERFOMRED BY ICP-MS/AAS

TESTED SAMPLE	RESULT (ppm)	CLIENT'S REQUIREMENT
SUBMITTED SAMPLE	(TRANSPARENT + INDIGO) PLASTIC: <10PPM	< 500 PPM

**REMARK:** ND = NOT DETECTE

DETECTION LIMIT = 10 PPM

\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 63

#### 2. TOTAL CADMIUM CONTENT IN SUBSTRATE

TEST REGULATION: EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23 TEST METHOD: WITH REF. TO EN112-ANALYSIS WAS PERFOMRED BY ICP-MS/AAS

TESTED SAMPLE RESULT (ppm)		CLIENT'S REQUIREMENT
SUBMITTED SAMPLE	(TRANSPARENT + INDIGO) PLASTIC: <10PPM	<100 PPM

**REMARK:** ND = NOT DETECTED

DETECTION LIMIT = 10 PPM

\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 23

## 3. BISPHENOL-A CONTENT TEST:

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)

TESTED COMPONENT	<u>RESULTS</u>	CLIENT'S REQUIREMENT
SUBMITTED SAMPLE	COMPLIES (TRANSPARENT + INDIGO) PLASTIC: ND	SHALL NOT CONTAIN ANY DETECTABLE LEVELS OF BISPHENOL A (BPA)

**DETECTION LIMIT: 0.1 PPM** 





NUMBER: DELH21013332- H

: 28TH SEP, 2021 DATE

### 4. OVERALL MIGRATION TEST:

TEST METHOD: IS 9845

## **TEST CONDITIONS AND RESULTS:**

MATERIAL PUT	SIMULANT	TEST CONDITION	RESULT IN (mg/dm²)	MAX. LIMIT
INTO CONTACT	USED		[1,2]	(mg/dm²)
	DISTILLED WATER	100°C FOR 02 HOURS	<5	<10
SUBMITTED SAMPLE	3% ACITIC ACID	100°C FOR 02 HOURS	<5	<10
	N-HEPTANE	49°C FOR 30 MIN.	<5	<10

**REMARK:** <= LESS THAN

RESULTS ARE GIVEN IN mg/dm<sup>2</sup>= Milligram per decimeter square

### **TESTED COMPONENT:**

1. TRANSPARENT PLASTIC

2. INDIGO LID

### 5. SPECIFIC MIGRATION OF HEAVY METALS TEST:

TEST METHOD: IS 9845

TEST CONDITION: 3% ACITIC ACID AT 100°C FOR 02 HOUR.

ELEMENT	RESULTS (mg/kg)	MAX. PERMISSIBLE LIMIT
ELEMEN 1	[1,2]	(mg/kg)
Barium (Ba)	<0.1	1.0
Cobalt (Co)	<0.01	0.10
Copper (Cu)	<1.0	5.0
Iron (Fe)	<5.0	48.0
Lithium (Li)	<0.1	0.6
Manganese (Mn)	<0.1	0.6
Zinc (Zn)	<1.0	25.0
Antimony (Sb)	<0.02	0.04

<sup>=</sup> LESS THAN

mg/kg = MILLIGRAM PER KILOGRAM

## TESTED COMPONENT:

- 1. TRANSPARENT PLASTIC
- 2. INDIGO LID



Tel: 0124-4503400,



NUMBER: DELH21013332- H

DATE : 28<sup>TH</sup> SEP, 2021

### 6. COLOUR MIGRATION TEST:

VISUAL OBSERVATION (SIMULANTS USED AS PER TEST METHOD: IS 9845)

## **TEST CONDITIONS AND RESULTS:**

MATERIAL PUT INTO CONTACT	SIMULANT USED	TEST CONDITION	RESULT [1]	MAX. LIMIT
SUBMITTED SAMPLE	DISTILLED WATER	100°C FOR 02 HOURS	NO COLOUR MIGRATED	THERE SHALL BE NO COLOR MIGRATED
	3% ACITIC ACID	100°C FOR 02 HOURS	NO COLOUR MIGRATED	THERE SHALL BE NO COLOR MIGRATED
	N-HEPTANE	49°C FOR 30 MIN.	NO COLOUR MIGRATED	THERE SHALL BE NO COLOR MIGRATED

### **TESTED COMPONENT:**

1. INDIGO LID

## 7. DISHWASHER SAFE TEST:

REFERENCE: IN-HOUSE TEST METHOD

## **TESTING CONDITIONS:**

(1) SELECTED CYCLE: NORMAL

(2) CYCLE DURATION: 120 MINUTES (APROX.)
(3) TEMPERATURE CONDITION: 60°C (APROX.)
(4) DETERGENT USED: CASCADE

(4) DETERGENT USED: CASCADE (5) NO. OF CYCLES: 10 CYCLES

TESTED SAMPLE	<u>OBSERVATION</u>	REQUIREMENT
SUBMITTED SAMPLE	<b>COMPLIES</b> NO VISUAL CHANGE OBSERVED	SHALL NOT SHOW ANY CHIPPING, CRACKING, GLAZE CRAZING OR OTHER VISUAL CHANGE IN APPEARANCE.





NUMBER: DELH21013332- H

DATE : 28<sup>TH</sup> SEP, 2021

## 8. MICROWAVE SAFE TEST:

(IN-HOUSE TEST METHOD)

MICROWAVE SAFE EVALUATION:

TESTED SAMPLE	OBSERVATION	REQUIREMENT
SUBMITTED SAMPLES	COMPLIES	SHALL NOT SHOW ANY CRACKING/CRAZING, MELTING, DEFORMATION OR OTHER UNUSUAL CHANGES. TEMPRATURE OF HANDLE OR SURFACE SHALL NOT EXCEED THE FOLLOWING LIMITS. Ceramic, Glass-Ceramic or Glass: 56°C Plastic: 60°C

### 9. FREEZER SAFE TEST:

(IN-HOUSE TEST METHOD)

## **TESTING CONDITIONS:**

(1) FREEZER TEMPERATURE: -18°C

(2) FREEZER EXPOSED PERIOD: 24 HOURS

TESTED SAMPLE	OBSERVATION	REQUIREMENT
SUBMITTED SAMPLE	COMPLIES	SHALL NOT SHOW ANY CRACK/DAMAGE/DEFORMATI ON





NUMBER: DELH21013332- H

DATE : 28<sup>TH</sup> SEP, 2021

### 10. AIR TIGHT TEST:

(IN-HOUSE TEST METHOD)

DURATION	SAMPLE AS RECIVED	SAMPLE AFTER FIRST WASH	REQUIREMENT
DAY- 0	122.7229	121.5460	
DAY- 1	122.9880	121.6726	
DAY- 2	123.2540	121.7699	~O 100/
DAY- 3	123.5162	121.9258	<0.10%
DAY- 4	123.7803	122.0510	
DAY- 5	124.0488	122.1791	
<u>D5 D0</u> D0	0.01	0.005	

\*

### # END OF TEST REPORT #

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

