

TEST REPORT



ORIGINAL SAMPLES

TEST REPORT

APPLICANT: ALL TIME PLASTICS PVT. LTD./ DAMAN
KACHIGA, CHAR RASTA, BEHIND STONE QUARY DAMAN (U.) 396210
ATTN: ZARIR PATEL / JYOTI

SAMPLE DESCRIPTION: THE SUBMITTED SAMPLE SAID TO BE – 404161 -Polka Container 503 (2500 ml)
- Purple

DATE RECEIVED : 08TH OCT, 2020
BUYER'S NAME : --
BUYING AGENT/ CONTACT : --
ORDER NO. : DAM-PO-GL-1920-900 DT. 26.12.2019
BARCODE : 8902084041615
STYLE NO. : 404161
COLOR : --
END USE : --
SEASON : --
COUNTRY OF ORIGIN : INDIA
COUNTRY OF DESTINATION : INDIA
MANUFACTURER'S NAME : ALL TIME PLASTICS PVT. LTD
CONTENT : --

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).


CONCLUSION:

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
SUBMITTED SAMPLE	DISHWASHER SAFE TEST (IN-HOUSE TEST METHOD)	M
	BISPHENOL-A CONTENT (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)	M
	OVERALL MIGRATION TEST (IS 9845)	M
	TOTAL LEAD CONTENT (AS PER EPA 3050B)	#
	TOTAL CADMIUM CONTENT (AS PER EPA 3050B)	#
	FREEZER TEST (AS PER IN HOUSE TEST METHOD)	M

NOTE: M = MEET CLIENT'S REQUIREMENT F = BELOW CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT N/A = NOT APPLICABLE

TESTING REMARK: AS CONFIRMED BY APPLICANT BOTH OF PRODUCT MADE BY SAME MATERIALS, NO TESTING CONDUCTED IN THIS TEST REPORT RESULT HAS BEEN INCORPORATED FROM REPORT NO. DELH19014685AS PER APPLICANT'S REQUEST

PREPARED & CHECKED BY
for INTERTEK INDIA PVT. LTD



SANJAY SADANA
TECHNICAL MANAGER – HARDLINE



TEST REPORT

TEST CONDUCTED:

1. DISHWASHER SAFE TEST:

(REFERENCE: IN-HOUSE TEST METHOD)

TESTING CONDITIONS:

- (1) SELECTED CYCLE: NORMAL
- (2) CYCLE DURATION: 120 MINUTES (APROX.)
- (3) TEMPERATURE CONDITION: 60°C (APROX.)
- (4) NO. OF CYCLES: 10

TESTED COMPONENT	RESULTS	CLIENT'S REQUIREMENT
SUBMITTED SAMPLE	COMPLIES NO VISUAL CHANGE OBSERVED	Shall not show any chipping, cracking, glaze crazing or other visual change in appearance.

2. BISPHENOL-A CONTENT:

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS/MS)

TESTED PART	OBSERVATION	CLIENT'S REQUIREMENT
SUBMITTED SAMPLE	COMPLIES Lid Plastic: Not Detected Container Plastic: Not Detected	Shall Not Contain Any Detectable Levels Of Bisphenol-A (BPA)

DETECTION LIMIT: 0.1 ppm

3. OVERALL MIGRATION TEST

(TEST METHOD: IS 9845)

TEST CONDITIONS AND RESULTS:

MATERIAL PUT INTO CONTACT	SIMULANT USED	TEST CONDITION	RESULT IN (mg/dm²)	MAX. LIMIT (mg/dm²)
SUBMITTED SAMPLE- LID PART	3% Acetic acid	40°C for 10 DAYS	<5	<10
	10% Ethanol & H ₂ O	40°C for 10 DAYS	<5	<10
	95% Ethanol	40°C for 10 DAYS	<5	<10
	Iso-Octane	20°C for 2 DAYS	<5	<10



TEST REPORT

<u>MATERIAL PUT INTO CONTACT</u>	<u>SIMULANT USED</u>	<u>TEST CONDITION</u>	<u>RESULT IN (mg/dm²)</u>	<u>MAX. LIMIT (mg/dm²)</u>
SUBMITTED SAMPLE-CONTAINER PART	3% Acetic acid	40°C for 10 DAYS	<5	<10
	10% Ethanol & H ₂ O	40°C for 10 DAYS	<5	<10
	95% Ethanol	40°C for 10 DAYS	<5	<10
	Iso-Octane	20°C for 2 DAYS	<5	<10

REMARK: <= LESS THAN
RESULTS ARE GIVEN IN mg/dm²

4. LEAD CONTENT
(AS PER EPA 3050B)

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	Lid Plastic: <10 PPM Transparent Plastic: <10 PPM	NOT PROVIDED

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION

5. CADMIUM CONTENT
(AS PER EPA 3050B)

<u>TESTED SAMPLE</u>	<u>RESULT (ppm)</u>	<u>CLIENT'S REQUIREMENT</u>
SUBMITTED SAMPLE	Lid Plastic: <10 PPM Transparent Plastic: <10 PPM	NOT PROVIDED

ND= NOT DETECTED
DETECTION LIMIT = 10 ppm
ppm = PARTS PER MILLION



TEST REPORT

6. FREEZER TEST

(AS PER IN HOUSE TEST METHOD)

TESTING CONDITIONS:

- 1 FREEZER TEMPERATURE: 0 °F
- 2 EXPOSURE PERIOD: 24 HOURS

TESTED SAMPLE	RESULTS	REQUIREMENT
SUBMITTED SAMPLE	COMPLIES (No visual change observed)	SHALL NOT SHOW ANY DISCOLORATION, DEFORMATION, CRACKING, CRAZING, CHIPPING OR OTHER CHANGE FROM THE ORIGINAL STATE.

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

