

**TEST REPORT**

NUMBER : DELH21009902

DATE : 07<sup>TH</sup> SEP, 2021



**ORIGINAL SAMPLE**

**TEST REPORT**

**APPLICANT:** ALL TIME PLASTICS PVT.LTD.  
PLOT NO. 377/1/1&2), KACHIGAM, CHAR RASTA, DAMAN - 396210

**ATTN:** ZARIR PATEL

**SAMPLE DESCRIPTION:** : DECORATIVE CHOPPING BOARD ( 340 X 240 X 12.5 MM)  
(AMETHYST, WHITE) (12 PC PK)

DATE RECEIVED : 25<sup>TH</sup> JULY, 2021  
BUYER'S NAME :  
BUYING AGENT/ CONTACT : --  
ITEM CODE : 407988-12  
HSN CODE : 39241090  
BARCODE : 8902084079885  
COLOR : --  
END USE : --  
COUNTRY OF ORIGIN : --  
COUNTRY OF DESTINATION : --  
MANUFACTURER'S NAME : ALL TIME PLASTICS PVT. LTD.

**TESTS CONDUCTED:** AS PER THE REQUEST BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

**CONCLUSION:**

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
<b>SUBMITTED SAMPLES</b>	<b>TOTAL LEAD CONTENT</b> (WITH REFERENE TO REGULATION (EC) NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63)	<b>M</b>
	<b>TOTAL CADMIUM CONTENT</b> (AS PER EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23)	<b>M</b>
	<b>BISPHENOL-A CONTENT TEST</b> (BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)	<b>M</b>
	<b>DISHWASHER SAFE TEST</b> (AS PER IN-HOUSE TEST METHOD)	<b>M</b>
	<b>OVERALL MIGRATION</b> (IS 9845)	<b>M</b>
	<b>SPECIFIC MIGRATION OF HEAVY METALS</b> (IS 9845)	<b>M</b>
	<b>COLOUR MIGRATION TEST:</b> (AS PER TEST METHOD: IS 9845)	<b>N/A</b>
	<b>SPECIFIC MIGRATION OF PHTHALATES</b> (SOLVENT EXTRACTION FOLLOWED BY GC-MSD ANALYSIS)	<b>M</b>

NOTE: M = MEET CLIENT'S REQUIREMENT      F = BELOW CLIENT'S REQUIREMENT  
# = NO SPECIFIED REQUIREMENT              N/A = NOT APPLICABLE

FOR INTERTEK INDIA PVT. LTD



SANJAY SADANA  
TECHNICAL MANAGER – HARDLINE

**TEST REPORT**

**TEST CONDUCTED:**

**1. TOTAL LEAD CONTENT IN SUBSTRATE**

TEST REGULATION: WITH REFERENCE TO EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 63

TEST METHOD: ANALYSIS WAS PERFORMED BY ICP-MS/AAS

<b><u>TESTED SAMPLE</u></b>	<b><u>RESULT (ppm)</u></b>	<b><u>CLIENT'S REQUIREMENT</u></b>
SUBMITTED SAMPLES	Transparent plastic: <10ppm White TPE material: <10ppm	< 500 ppm

**REMARK:** ND = NOT DETECTED  
DETECTION LIMIT = 10 PPM  
\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 63

**2. TOTAL CADMIUM CONTENT IN SUBSTRATE**

TEST REGULATION: EC NO. 1907/2006 (REACH) AND ITS AMENDMENTS, ANNEX XVII, ENTRY 23

TEST METHOD: WITH REF. TO EN112-ANALYSIS WAS PERFORMED BY ICP-MS/AAS

<b><u>TESTED SAMPLE</u></b>	<b><u>RESULT (ppm)</u></b>	<b><u>CLIENT'S REQUIREMENT</u></b>
SUBMITTED SAMPLES	Transparent plastic: <10ppm White TPE material: <10ppm	<100 ppm

**REMARK:** ND = NOT DETECTED  
DETECTION LIMIT = 10 PPM  
\*REQUIREMENT IS REFERED FROM REACH ANNEX XVII, ENTRY 23

**3. BISPHENOL-A CONTENT TEST:**

(BY SOLVENT EXTRACTION FOLLOWED BY LC-MS / MS)

<b><u>TESTED COMPONENT</u></b>	<b><u>RESULTS</u></b>	<b><u>CLIENT'S REQUIREMENT</u></b>
SUBMITTED SAMPLES	<b>COMPLIES</b> Transparent plastic: ND White TPE material: ND	SHALL NOT CONTAIN ANY DETECTABLE LEVELS OF BISPHENOL A (BPA)

DETECTION LIMIT: 0.1 PPM

**TEST REPORT**

**4. DISHWASHER SAFE TEST:**

REFERENCE: IN-HOUSE TEST METHOD

**TESTING CONDITIONS:**

- (1) SELECTED CYCLE: NORMAL
- (2) CYCLE DURATION: 120 MINUTES (APROX.)
- (3) TEMPERATURE CONDITION: 60°C (APROX.)
- (4) DETERGENT USED: CASCADE
- (5) NO. OF CYCLES: 10 CYCLES

<b><u>TESTED SAMPLE</u></b>	<b><u>OBSERVATION</u></b>	<b><u>REQUIREMENT</u></b>
<b>SUBMITTED SAMPLES</b>	<b>COMPLIES</b> NO VISUAL CHANGE OBSERVED	SHALL NOT SHOW ANY CHIPPING, CRACKING, GLAZE CRAZING OR OTHER VISUAL CHANGE IN APPEARANCE.

**5. OVERALL MIGRATION TEST:**

TEST METHOD: IS 9845

**TEST CONDITIONS AND RESULTS:**

<b>MATERIAL PUT INTO CONTACT</b>	<b>SIMULANT USED</b>	<b>TEST CONDITION</b>	<b>RESULT IN (mg/dm<sup>2</sup>)</b>	<b>MAX. LIMIT (mg/dm<sup>2</sup>)</b>
			<b>[1]</b>	
<b>SUBMITTED SAMPLES</b>	DISTILLED WATER	70°C FOR 02 HOURS	<5	<10
	3% ACITIC ACID	70°C FOR 02 HOURS	<5	<10
	10% ETHANOL	70°C FOR 02 HOURS	<5	<10
	50% ETHANOL	70°C FOR 02 HOURS	<5	<10
	N-HEPTANE	38°C FOR 30MIN.	<5	<10

**REMARK:** <= LESS THAN

RESULTS ARE GIVEN IN mg/dm<sup>2</sup>= Milligram per decimeter square

**TESTED COMPONENT:**

1. TRANSPARENT PLASTIC CHOPPING BOARD, WHITE BORDER



**TEST REPORT**

**6. SPECIFIC MIGRATION OF HEAVY METALS TEST:**

TEST METHOD: IS 9845  
TEST CONDITION: 3% ACITIC ACID AT 70°C FOR 02 HOUR.

ELEMENT	RESULTS (mg/kg)	MAX. PERMISSIBLE LIMIT (mg/kg)
	[1]	
Barium (Ba)	<0.1	1.0
Cobalt (Co)	<0.01	0.05
Copper (Cu)	<1.0	5.0
Iron (Fe)	<5.0	48.0
Lithium (Li)	<0.1	0.6
Manganese (Mn)	<0.1	0.6
Zinc (Zn)	<1.0	25.0
Antimony (Sb)	<0.02	0.04

< = LESS THAN  
mg/kg = MILLIGRAM PER KILOGRAM

**TESTED COMPONENT:**

1. TRANSPARENT PLASTIC CHOPPING BOARD, WHITE BORDER

**7. SPECIFIC MIGRATION OF PHTHALATE:**

SOLVENT EXTRACTION FOLLOWED BY GC-MSD ANALYSIS

TEST RESULT:  
TEST CONDITION: 3% ACITIC ACID AT 70°C FOR 02 HOUR.

TESTED COMPONENTS	RESULT (PPM)
	[1]
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DnOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND

Limit: Individual Less than 0.1% (1000 ppm)

**TESTED COMPONENT:**

1. TRANSPARENT PLASTIC CHOPPING BOARD WHITE BORDER

\*\*\*\*\*

**# END OF TEST REPORT #**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

